

# Data Sheet

## DUTEX - 135

GEOTEXTILE 100% Polypropylene, needle punched, non-woven, UV stabilized


Applications of non woven, needle punched Geotextile




Road




Railroad




Coastal




Pipeline



Landfill



Roofing



Slope

Properties *	Standard		Unit	DUTEX-135
<b>MECHANICAL</b>				
Thickness	ASTM D 5199	ISO 9863	mm.	0.85
Grab Strength	ASTM D 4632		N.	500
CBR Puncture Strength	ASTM D 6241	ISO 12236	N.	1400
Puncture Resistance	ASTM D 4833		N.	300
Grab Elongation	ASTM D 4632		%	> 50
Trapezoidal Tear Resistance	ASTM D 4533		N.	180
Mullen Burst	ASTM D 3786		kPa	1200
Tensile Strength	ASTM D 4595	ISO 10319	kN / m	7.5
<b>HYDRAULIC</b>				
AOS **	ASTM D 4751	ISO 12956	mm.	0.09
Permittivity	ASTM D 4491	ISO 11058	Sec <sup>-1</sup>	2.00
Permeability	ASTM D 4491	ISO 11058	cm/s	0.22
Flow Rate – 10 cm head	ASTM D 4491	ISO 11058	l/sq.mt/s	180
<b>ULTRA VIOLET</b>				
UV Stability (@ 150hrs)	ASTM D 4355	ISO 12959	%	>85
<b>Roll Dimensions</b>				
Roll Width			Mt	5.6

\*: Mean Average Roll Value (MARV)

\*\* : Maximum Average Roll Value

The rights are reserved to modify the present data sheet without prior notice