

Data Sheet

DUTEX - 150

GEOTEXTILE 100% Polypropylene, needle punched, non-woven, UV stabilized


Applications of non woven, needle punched Geotextile




Road




Railroad




Coastal




Pipeline



Landfill



Roofing



Slope

Properties *	Standard		Unit	DUTEX-150
MECHANICAL				
Thickness	ASTM D 5199	ISO 9863	mm.	1.00
Grab Strength	ASTM D 4632		N.	600
CBR Puncture Strength	ASTM D 6241	ISO 12236	N.	1600
Grab Elongation	ASTM D 4632		%	>50
Trapezoidal Tear Resistance	ASTM D 4533		N.	200
Mullen Burst	ASTM D 3786		kPa	1400
Tensile Strength	ASTM D 4595		kN / m	8.5
HYDRAULIC				
AOS **	ASTM D 4751	ISO 12956	mm.	0.09
Permittivity	ASTM D 4491	ISO 11058	Sec ⁻¹	1.80
Flow Rate - 10cm head	ASTM D 4491	ISO 11058	l/sq.mt/s	170
ULTRA VIOLET				
UV Stability (@ 150hrs)	ASTM D 4355	ISO 12959	%	>85
Roll Dimensions				
Roll Width			Mt	5.60

*: Mean Average Roll Value (MARV)

** : Maximum Average Roll Value

The rights are reserved to modify the present data sheet without prior notice